

cf2

exported from elementalcolor.com · export date: May 28, 2026

February 4, 2025 · Falls Church, VA · copper ferrite

● currently shipping from this batch

overview

zero time: Feb 4, 2025, 08:16 PM · duration: 5.7h

synthesis



charge

35.436g charge

events

- t+0.0h Boat in / furnace zero-time (4:16P local).
- t+1.0h 922C reached at 01:02 elapsed.
- t+5.7h 950C; power off at 05:42 elapsed.

Elapsed-time log: 00:00 96C; 00:24 414C; 00:44 715C; 01:02 922C; 05:42 950C power off.

product

yield 32.5861 g (92.0%)
expected 35.436 g
variance -2.85 g

notes

- 32.5861g out of 35.436g charge (92% yield).

For informational purposes only. Batch data reflects recorded conditions and is not a guarantee of specifications.

© 2026 elemental color, an exotic inorganics llc brand · [privacy](#) · [legal](#) · made with love in falls church, va